

LEVISO

- 高級感のあるディムアウト生地に合わせた同色の2重織り裏地で、統一感のある外観を実現
- 有害物質を含まないエコテックス規格100の認証を取得
- 60℃までのウォッシュابل製品
- 優れた音響特性

アプリケーション



織物表示

	Dimout
	ポリエステル
	370 g/m ²
	0.80 mm
	295 cm
	300 cm

洗濯表示



技術特性

	4-5
	Alpha-w = 0.75 / 0.90
	難燃性
	クロス処理のみ
	クロス処理のみ
	Oeko-Tex
	特別色 1'000 m

難燃性

Class 1 (EN 13773)
Class 1 (UNI 9176/77)
M1 (NF P 92-503/5/7)
Type B (BS 5867-2)



Leviso

光学および太陽係数 (± 5%, DIN EN 410)

Colour	T _v	T _s	R _s	A _s	T _{uv}	F _c	g _{tot}
1	1.9	2.2	62.0	35.8	0.10	0.52	0.38
2	1.9	2.2	62.0	35.8	0.10	0.52	0.38
3	1.9	2.2	62.0	35.8	0.10	0.52	0.38
5	1.9	2.2	62.0	35.8	0.10	0.52	0.38
7	0.0	1.0	38.8	60.2	0.00	0.67	0.48
8	0.0	1.0	40.9	58.1	0.00	0.66	0.47
9	0.1	1.2	45.9	52.9	0.00	0.63	0.45
11	0.0	1.2	39.5	59.3	0.00	0.67	0.48
12	0.2	1.2	54.2	44.6	0.00	0.57	0.41
14	0.1	1.2	45.9	52.9	0.00	0.63	0.45
15	0.1	1.2	45.9	52.9	0.00	0.63	0.45
18	0.2	1.2	54.2	44.6	0.00	0.57	0.41
19	0.1	1.1	49.7	49.2	0.00	0.60	0.43
21	0.3	1.4	61.4	37.2	0.00	0.53	0.38
23	1.9	2.2	62.0	35.8	0.10	0.52	0.38
24	0.3	1.4	61.4	37.2	0.00	0.53	0.38
25	0.1	1.2	45.9	52.9	0.00	0.63	0.45
26	0.0	1.0	40.9	58.1	0.00	0.66	0.47
28	0.0	1.0	40.9	58.1	0.00	0.66	0.47

T_v Visible light transmission

T_s Solar transmission

R_s Solar reflectance


A_s Solar absorption

T_{uv} UV transmission


F_c Shading factor

g_{tot} Total g-value


Fc + gtot: ガラスで計算した値: 0.72 / Ug = 1.6 W/m² K, DIN EN 13363-1

Leviso



1



2



3




5



7




8



9




11



12



14



15



18



19



21



23



24



25



26



28