

OSCURANTE

- 均一感のある外観を見せる為裏表の色を統一、心地よい手触りの滑らかなディムアウト生地
- 有害物質を含まないエコテックス規格100の認証を取得
- 72℃までのウォッシュابل製品
- 優れた音響特性

アプリケーション



織物表示

	Dimout
	ポリエステル
	250 g/m ²
	0.45 mm
	295 cm
	300 cm

洗濯表示



技術特性

	5-6
	Alpha-w = 0.60
	難燃性
	湿度の高い場所でも使用可能
	Waveに対応
	Oeko-Tex
	特別色 200 m

難燃性

Class 1 (EN 13773)
Class 1 (UNI 8456)
Type B (BS 5867-2)



Oscurante

光学および太陽係数 (± 5%, DIN EN 410)

Colour	T _V	T _S	R _S	A _S	F _C	g _{tot}
328	0.2	0.3	56.8	42.9	0.56	0.40
331	0.0	0.2	45.4	54.4	0.63	0.45
334	0.1	0.2	54.1	45.7	0.57	0.41
337	0.0	0.3	31.5	68.2	0.72	0.52
338	0.0	0.2	28.1	71.7	0.74	0.53
339	0.0	0.2	33.1	66.7	0.71	0.51
340	0.0	0.2	40.5	59.3	0.61	0.48
343	0.0	0.2	32.3	67.5	0.71	0.51
344	0.0	0.2	31.6	68.2	0.72	0.52
752	0.0	0.2	41.9	57.9	0.65	0.47
756	0.0	0.2	47.7	52.1	0.62	0.44
757	0.0	0.2	37.4	62.4	0.68	0.49

T_V Visible light transmission

R_S Solar reflectance

F_C Shading factor

T_S Solar transmission

A_S Solar absorption

g_{tot} Total g-value

F_C + g_{tot}: ガラスで計算した値: 0.72 / U_g = 1.6 W/m² K, DIN EN 13363-1

Oscurante

328



331



334



337



338



339



340



343



344



752



756



757