

POLYFLAX

- 天然繊維のリネンの風合いを持つポリエステル生地です。
- 有害物質を含まないエコテックス規格100の認証を取得
- 72℃までのウォッシュابل製品

アプリケーション



織物表示

	Transparent
	ポリエステル
	100 g/m ²
	0.47 mm
	325 cm
	330 cm

洗濯表示



技術特性

	5
	難燃性
	湿度の高い場所でも使用可能
	Waveに対応
	Oeko-Tex
	特別色 120 m

難燃性

Class 1 (EN 13773)
Class 1 (UNI 8456)
Type B (BS 5867-2)



Polyflax

光学および太陽係数 (± 5%, DIN EN 410)

Colour	T _v	T _s	R _s	A _s	T _{UV}	F _c	g _{tot}
100	59.9	58.7	37.4	3.9	34.9	0.73	0.52
120	54.2	56.0	36.5	7.5	46.9	0.73	0.53
160	39.7	48.8	30.5	20.7	38.6	0.76	0.55
220	53.1	56.0	35.9	8.1	48.0	0.73	0.53
240	44.7	51.5	33.5	15.0	43.4	0.75	0.54
740	35.2	47.5	25.8	26.7	39.1	0.79	0.57
760	31.8	46.1	24.9	29.0	37.9	0.80	0.57
940	28.7	39.3	30.9	29.8	26.3	0.75	0.54

T_v Visible light transmission

R_s Solar reflectance

T_{UV} UV transmission

g_{tot} Total g-value


T_s Solar transmission

A_s Solar absorption


F_c Shading factor

F_c + g_{tot}: ガラスで計算した値: 0.72 / Ug = 1.6 W/m² K, DIN EN 13363-1


Polyflax




100




120




160




220




240



740



760



940